

บทคัดย่อ

วัตถุประสงค์ของชุดโครงการวิจัยนี้คือการประเมินศักยภาพของชั้นเกลือหินชุดมหาสารคามเพื่อใช้เป็นแหล่งกากเก็บของเสียจากภาคอุตสาหกรรม ซึ่งได้ดำเนินการในหลายประเด็นรวมไปถึงผลกระทบของอุณหภูมิ (สูงถึง 200°C) ที่สูงขึ้นต่อกำลังดึงของเกลือหิน ศักยภาพเชิงกลศาสตร์ของวัสดุที่ใช้อุตช่องเหมือง (เกลือบด ส่วนผสมของเกลือบดกับเบนโทไนต์ และชีเมนต์ทันเค็ม) และความหนาแน่นของแผ่นกระเบื้องเซรามิกที่เคลือบด้วยสารปูรงพิเศษ CZS (CaO , ZrO_2 และ SiO_2) ภายใต้สภาวะความเป็นกรดเกลือ ผลการทดสอบระบุว่าค่ากำลังรับแรงกด ค่ากำลังรับแรงดึง และความยืดหยุ่นของเกลือหินจะลดลงเมื่ออุณหภูมิสูงขึ้น ภายใต้แนวคิดของพลังงานความเครียดสามารถสรุปได้ว่า พลังงานความเครียดเปียงเปนที่สำคัญและมีผลต่อความสามารถด้านการรับแรงดึงของเกลือหิน สามารถให้ข้อมูลเชิงลึกของอุณหภูมิที่สูงขึ้นตามเวลาภายใต้การอัดตัว ส่วนผสมของเบนโทไนต์และเกลือบดที่ผสมกับน้ำเกลือร้อยละ 5 ถึง 10 โดยน้ำหนัก จะสามารถอัดตัวได้อย่างมีประสิทธิภาพและให้ค่ากำลังเฉือนที่สูงขึ้นตามเวลาภายใต้การอัดตัว สำหรับการทดสอบน้ำหนัก ใช้วัสดุผสมที่มีความเหมาะสมที่จะใช้เป็นวัสดุอุตสาหกรรม เช่น เกลือบดที่อ่อนนุ่ม สามารถอัดตัวได้อย่างมีประสิทธิภาพและให้ค่ากำลังเฉือนที่สูงขึ้นตามเวลาภายใต้การอัดตัว 30:70 และให้ค่ากำลังเฉือนสูงสุดและค่าความซึมผ่านต่ำสุด โดยเกลือบดมีขนาด 3 ถึง 4 มิลลิเมตร และมีปริมาณน้ำเกลือร้อยละ 20 โดยน้ำหนัก ซึ่งวัสดุผสมนี้มีความเหมาะสมที่จะใช้เป็นวัสดุมากับในตำแหน่งที่ต้องการลดการไหลเย็นของน้ำเกลือหรือน้ำบาดาลเพื่อไม่ให้ร้อนต่อตัวของน้ำ ซึ่งเมือง ผลกระทบทดสอบยังระบุปอร์ตแลนด์ชีเมนต์ที่ใช้อยู่ทั่วไปที่ผสมสารต่อต้านคลอรีนสามารถให้ความเสียดทานที่ดีกว่าเกลือบดกับชีเมนต์ที่สูงพอ ผลกระทบทดสอบการดันตัวในหลุมจะให้ค่าความเสียดทานดังกล่าวที่สูงกว่าผลกระทบทดสอบกำลังเฉือนแบบตรง เหตุผลเนื่องจากอัตราส่วนของปัจจัยที่ทำให้ชีเมนต์อุดในหลุมจะบานตัวติดกับผนังของหลุมจะทำให้แรงดันในแนวแกน เกลือหินล่างของชุดหินมหาสารคามมีการแผ่กระจายความลึกและความหนาที่เหมาะสมสำหรับใช้เป็นที่กากเก็บของเสียจากภาคอุตสาหกรรม ตำแหน่งที่ต้องการทดสอบในคราวที่ยกมาเป็นตัวอย่างในชุดโครงการวิจัยนี้มีวัตถุประสงค์เพื่อแสดงถึงการออกแบบโครงสร้างและช่องเหมืองแห้งที่แตกต่างกันสำหรับความลึกและความหนาของชั้นเกลือหินที่แตกต่างกัน

Abstract

The objective of this research program is to assess the performance of the Maha Sarakham rock salt for use as a host rock for the industrial waste repository. Several aspects of the performance assessment for the industrial waste disposal include the effects of elevated temperatures (up to 200 Celsius) on the compressive and tensile strengths of the salt, the mechanical performance of sealing materials (crushed salt, mixtures of crushed salt and bentonite, and saline resistant cement), and durability of the ceramic tiles coating with CZS (CaO , ZrO and SiO_2) under saline environment. The results indicate that the salt compressive and tensile strengths and elasticity decreases with increasing temperature. Based on the concept of the strain energy density the distortional strain energy density at failure and at dilation can be derived as a function of the mean strain energy. The energy criteria can well describe the failure and dilation of salt under various temperatures. The pre-compressed crushed salt and compacted mixtures of crushed salt and bentonite are recommended for use as sealing materials. The crushed salt with 5–10% brine content can be effectively consolidated, and providing shear strength that increases with time. The compacted bentonite-crushed salt weight ratio of 30:70 with grain sizes ranging from 2–4 mm and brine content of 20% gives the greatest shear strength and lowest permeability. It is suitable as backfill materials to minimize the brine or groundwater flow in the leakage cracks and solution channels. The commercial grade Portland cement with chlorine resistant agent can give sufficiently high mechanical resistance at the salt–cement interface. The borehole push-out test results yield greater interface resistance than those obtained from the direct shear testing due to the effect of the Poisson's ratio. The Lower salt member of the Maha Sarakham formation is suitable for the industrial waste disposal in terms of the extent, depth and thickness. The specific locations in the Khorat basin have been given as examples here to demonstrate that different tentative designs of the solution caverns and dry mine openings can be implemented for different depths and thickness of the hosted salt.