

บรรณชัย อุตสาห : ผลของศักย์การเกิดแกรไฟฟ์ ต่อการขยายตัวของยูเทกติกในเหล็กหล่อ
เทา (EFFECT OF GRAPHITIZATION POTENTIAL ON THE EUTECTIC EXPANSION IN GRAY IRON) อาจารย์ที่ปรึกษา : ผู้ช่วยศาสตราจารย์ ดร.สารัมภ์
บุญมี, 137 หน้า.

งานวิจัยนี้มีวัตถุประสงค์เพื่อศึกษาศักย์การเกิดแกรไฟฟ์ ตั้งแต่การเกิดในเหล็กหล่อขาว
เหล็กหล่อมอตเติล ไปจนถึงเหล็กหล่อเทา และศึกษาระดับของการทำอินเน็อกคูเลชันต่อพุติกรรม
การหดและการขยายตัวในระหว่างการแข็งตัวของเหล็กหล่อเทา อันเนื่องมาจากสัณฐานวิทยาของ
แกรไฟฟ์ที่เปลี่ยนไปด้วยวิธีการวัดการเคลื่อนที่เชิงเส้นและการวิเคราะห์ทางความร้อน โดยใช้ชุด
อุปกรณ์ที่ประกอบด้วยแบบหล่อทรายฟูรานเรซินทรงกลมขนาดเส้นผ่านศูนย์กลาง 76.2 มิลลิเมตร
ที่ผลิตจากเครื่องพิมพ์ 3 มิติ ด้วยกรรมวิธีแอคเดคิทิฟและหุ้มด้วยแบบเหล็กกล้า โดยมีเทอร์โมคัปเปิล
และอุปกรณ์วัดการเคลื่อนที่เชิงเส้นสำหรับวัดอุณหภูมิและการเคลื่อนที่ในระหว่างการแข็งตัวไปใน
เวลาเดียวกัน จากนั้นได้หล่อเหล็กหล่อ 2 ชุดการศึกษา โดยชุดแรกศึกษาศักย์ของการเกิดแกรไฟฟ์
ที่มีปริมาณซิลิคอนตั้งแต่ 0.2 0.47 0.95 1.49 1.78 1.80 และ 2.06 ร้อยละ โดยนำหัวน้ำหนักจากการ
ทดลองพบว่าปริมาณและเวลาที่ใช้ในการขยายตัวของแกรไฟฟ์เพิ่มขึ้นและการหดตัวภายหลังจาก
การขยายตัวของแกรไฟฟ์ลดลงตามศักย์ของการเกิดแกรไฟฟ์และcarbon content ที่เพิ่มขึ้น โดยมี
ปริมาณการขยายตัวอยู่ในช่วง 0.14 – 1.36 มิลลิเมตร และเวลาที่ใช้ในการขยายตัวมีค่าอยู่ระหว่าง
162 – 471 วินาที ในชุดการศึกษาที่ 2 ศึกษาผลของการทำอินเน็อกคูเลชันที่ปริมาณร้อยละ 0.1 0.2
และ 0.3 พบว่าเงื่อนไขที่มีปริมาณcarbon content อยู่ระหว่าง 0.1 และ 0.2 น้ำหนักตัวของแกรไฟฟ์มากกว่า

AUTTACHAI UTSAJAI : EFFECT OF GRAPHITIZATION POTENTIAL ON
THE EUTECTIC EXPANSION IN GRAY IRON. THESIS ADVISOR :
ASST. PROF. SARUM BOONMEE, PhD., 137 PP.

SOLIDIFICATION BEHAVIOR/GRAFHTIZATION POTENTIAL/CAST IRON/
LINEAR DISPLACEMENT/SOLID FRACTION.

The objective of this research is to study the effect of the graphitization potential and the level of inoculation on the expansion and contraction in gray irons (GI). The special equipment was created for this work. The spherical furan resin additive-manufactured sand molds dimensions 76.2 mm were encased with the steel jackets to minimize the mold-wall movement. The mold was equipped with a thermocouple (type S) and a Linear Variable Differential Transformer (LVDT) to monitor the temperature change and displacement during solidification simultaneously. Irons with various graphitization potential that followed %Si 0.2, 0.47, 0.95, 1.49, 1.78, 1.80 and 2.06 were produced. It was found that the graphite expansion and the graphite expansion time increased with increasing graphitization potential. In addition, the contraction after the expansion of graphite decreased with increasing graphitization potential and carbon equivalent ranging from 0.14 - 1.36 mm 0.2 - 1.8 mm. for the graphite expansion and 162 - 471 s. for the graphite expansion time. The experiment with the level of inoculation demonstrated that the graphite expansion and the graphite expansion time increased with increasing carbon equivalent.

School of Metallurgical Engineering

Academic Year 2019

Student's Signature _____ Auttachai Utsojai

Advisor's Signature _____ Sarum