

วิทยุกร สมิงทอง : อิทธิพลของสภาวะเปียกสลับแห้งต่อกำลังอัดของตะกอนดินประปา-
เถ้าลอยจีโอ โพลิเมอร์ (INFLUENCE OF WETTING-DRYING CYCLES ON
COMPRESSIVE STRENGTH OF SLUDGE-FLY ASH GEOPOLYMER) อาจารย์ที่
ปรึกษา : ศาสตราจารย์ ดร.สุขสันต์ หอพิบูลสุข, 50 หน้า.

ตะกอนดินเถ้าลอยจีโอโพลิเมอร์เป็นส่วนผสมระหว่างตะกอนดินประปา (Sludge) กับ
เถ้าลอย (Fly ash) และสารละลายอัลคาไลน์ (activator) ซึ่งจัดเป็นวัสดุก่อสร้างเขียว (Green
material) ตะกอนดินประปาได้จากโรงงานผลิตน้ำบางเขน เถ้าถ่านหินได้จากโรงไฟฟ้าแม่เมาะ
จังหวัดลำปาง สารละลายอัลคาไลน์เป็นส่วนผสมของ โซเดียมซิลิเกต (Na_2SiO_3) และ
โซเดียมไฮดรอกไซด์ (NaOH) งานวิจัยนี้จะศึกษาอิทธิพลของสภาวะเปียกสลับแห้งต่อกำลังอัดของ
ดินตะกอน-เถ้าลอยจีโอโพลิเมอร์ ซึ่งเป็นคุณสมบัติทางวิศวกรรมที่สำคัญในการออกแบบความ
คงทนของวัสดุก่อสร้าง อัตราส่วนระหว่างสารละลายอัลคาไลน์ต่อเถ้าลอยที่ใช้ในงานวิจัยนี้เท่ากับ
1.6 อัตราส่วน $\text{Na}_2\text{SiO}_3/\text{NaOH}$ เท่ากับ 50:50 70:30 80:20 90:10 และ 100:0 ความร้อนในการ
กระตุ้นตัวอย่างเท่ากับ 65 75 85 และ 95°C และระยะเวลาบ่มเท่ากับ 24 48 72 96 และ 120 ชั่วโมง
การเตรียมตัวอย่างจีโอโพลิเมอร์สำหรับการทดสอบเปียกสลับแห้งกระทำตามมาตรฐาน ASTM D
559 – 03 จำนวนรอบของสภาวะเปียกสลับแห้งเท่ากับ 1 3 6 9 และ 12 รอบ ผลการศึกษาพบว่า
อัตราส่วน $\text{Na}_2\text{SiO}_3/\text{NaOH}$ เหมาะสมที่ให้กำลังอัดสูงของตัวอย่างสูงสุดคือ 90:10 ซึ่งให้กำลังอัดสูง
กว่า 2.5 เมกกะปาสกาล (ค่ายอมให้สำหรับบล็อกไม่รับแรงอัด ตามมาตรฐาน
ผลิตภัณฑ์อุตสาหกรรมไทย) ร้อยละของการดูดซึมน้ำของตะกอนดิน-เถ้าลอยจีโอโพลิเมอร์ที่
สัดส่วนเหมาะสมและบ่มด้วยความร้อนต่ำกว่า 95°C มีค่าต่ำกว่า 14.3 (ค่ายอมให้ สำหรับบล็อกรับ
และไม่รับน้ำหนัก) อุณหภูมิและระยะเวลาบ่มที่เหมาะสม (ให้กำลังอัดสูงสุด) คือ 85°C และ 72 ชั่วโมง
ซึ่งให้กำลังอัดของตะกอนดิน-เถ้าลอยจีโอโพลิเมอร์สูงกว่า 7.0 เมกกะปาสกาล (ค่ายอมให้สำหรับ
บล็อกรับแรงอัด ตามมาตรฐานผลิตภัณฑ์อุตสาหกรรมไทย) ที่รอบเปียกสลับแห้งจำนวน 12 รอบ
งานวิจัยนี้ได้สร้างสมการทำนายกำลังอัดที่รอบเปียกสลับแห้งต่างๆ ในพจน์ของกำลังอัดแบบแช่น้ำ
และจำนวนรอบเปียกสลับแห้ง ซึ่งเป็นประโยชน์อย่างมากในการออกแบบสัดส่วน เพื่อให้ได้
ผลิตภัณฑ์ที่มีกำลังอัดตามต้องการที่จำนวนรอบเปียกสลับแห้งที่กำหนด

สาขาวิชาวิศวกรรมโยธา

ปีการศึกษา 2556

ลงชื่อนักศึกษา _____

ลงชื่ออาจารย์ที่ปรึกษา _____

WISANUKHORN SAMINGTHONG : INFLUENCE OF WETTING-DRYING
CYCLES ON COMPRESSIVE STRENGTH OF SLUDGE-FLY ASH
GEOPOLYMER. THESIS ADVISOR : PROF. SUKSUN HORPIBULSUK,
Ph.D., 50 PP.

GEOPOLYMER/SLUDGE/FLY ASH

Sludge-Fly Ash Geopolymer, which is a mixture of sludge, fly ash (FA) and liquid alkaline activator, is green construction material. Sludge was obtained from the Bang Khen water treatment plant of the Metropolitan Water Work Authority of Thailand (MWA). FA was obtained from the Mae Moh power plants of the Electricity Generating Authority of Thailand (EGAT). A liquid alkaline activator, L is a mixture of sodium silicate solution (Na_2SiO_3) and sodium hydroxide solution (NaOH). This research studies influences of wetting-drying (w-d) cycles on compressive strength of sludge-fly ash geopolymer, which is an important parameter for service life design. The $\text{Na}_2\text{SiO}_3/\text{NaOH}$ ratio used was 50:50, 70:30, 80:20, 90:10 and 100:0. Heat temperatures were 65, 75, 85 and 95°C and heat durations were 24, 48, 72, 96 and 120 hours. The samples w-d cycle test were prepared according to the American Standard for Testing and Materials (ASTM D 559 – 03). Number of cycles were 1, 3, 6, 9 and 12 cycles. Results show that the optimal $\text{Na}_2\text{SiO}_3/\text{NaOH}$, providing the highest strength, is found at 90:10 in which the strength is greater than 2.5 MPa (allowable strength for non-bearing masonry units specified by Thailand Industrial Standard). The water absorption of the samples at this optimal $\text{Na}_2\text{SiO}_3/\text{NaOH}$ with heat temperature lower than 95°C is lower than 14.3% (allowable value for both bearing and non-bearing masonry units). The optimal heat temperature and duration,

providing highest strength, is 85°C and 72 hours. The 12 w-d cycle strength of samples prepared at optimal $\text{Na}_2\text{SiO}_3/\text{NaOH}$ and heat temperature and heat duration is greater than 7.0 MPa, which is the allowable value for bearing masonry unit. Finally, a predictive w-d cycle strength equation is proposed in terms of initial soaked strength and number of w-d cycle. The proposed equation facilitates mix design to attain the required strength at a target w-d cycle.



School of Civil Engineering

Academic Year 2013

Student's Signature_____

Advisor's Signature_____