พิมพ์ชนก เสริฐสูงเนิน : การใช้วัสดุฝุ่นแอสฟัลท์เหลือทิ้งร่วมกับเถ้าลอยในวัสดุซีเมนต์ ผสม (THE USE OF ASPHALT WASTE DUST AND FLY ASH IN CEMENT- MIXED MATERIALS) อาจารย์ที่ปรึกษา : รองศาสตราจารย์ ดร. จิรัชญา อายะวรรณา , 64 หน้า

## คำสำคัญ : วัสดุซีเมนต์ผสม/ฝุ่นแอสฟัลท์เหลือทิ้ง/เถ้าลอย/ค่ากำลังรับแรงอัด/การบ่ม

้จากปัญหาด้านสิ่งแวดล้อมในกา<mark>รปล</mark>ดปล่อยก๊าซคาร์บอนไดออกไซด์จากกระบวนการ **ผลิตปูนซีเม**นต์ นำมาสู่การพัฒนาวัสดุก่อส<mark>ร้างแบบ</mark>ยั่งยืนเพื่อลดปริมาณการใช้ปูนซีเมนต์ลง โดย ้ศึกษาวัสดุซีเมนต์ผสมที่ผลิตจากปูนซีเมนต์<mark>ปอ</mark>ร์<mark>ตแล</mark>นด์ชนิดที่ 1 ร่วมกับฝุ่นแอสฟัลท์เหลือทิ้งจาก โรงงานผลิตแอสฟัลท์คอนกรีตและเถ้าลอ<mark>ยจ</mark>ากการเ<mark>ผ</mark>าถ่านหินในการผลิตไฟฟ้า ชิ้นงานเตรียมจาก ู ปูนซีเมนต์ปอร์ตแลนด์ชนิดที่ 1 ร้อยละ 50 <mark>โ</mark>ดยน้ำหนั<mark>ก</mark> ร่วมกับฝุ่นแอสฟัลท์เหลือทิ้งและเถ้าลอยร้อย ละ 0 - 50 โดยน้ำหนัก ทดสอบระยะ<mark>เวลา</mark>การก่อตัวแ<mark>ละค่</mark>ากำลังรับแรงอัดหลังจากบ่มวัสดุซีเมนต์ ้ผสมตามมาตรฐานอุตสาหกรรม โดย<mark>วัสดุ</mark>ชีเม<sup>ุ</sup>นต์ผสมจะ<mark>ถูกบ</mark>ุ่มในสภาวะน้ำปูนขาวอิ่มตัวและการบุ่ม ภายใต้เงื่อนไขห่อหุ้มด้วยแผ่นฟิ<mark>ล์มพ</mark>ลาสติก<mark>เป็นระ</mark>ยะเวลา <mark>3 วัน</mark> 7 วัน และ 28 วัน หลังจากนั้นทำ การวิเคราะห์โครงสร้างระดับจุ<mark>ลภาค</mark>และการเปลี่ยนแปลงเฟสใ<mark>นตัว</mark>อย่างวัสดุซีเมนต์ผสมหลังทดสอบ ระยะเวลาการก่อตัวระยะต้นของวัสดุชีเมนต์ผสมทุกสูตรพบว่าผ่านเกณฑ์มาตรฐาน มอก. 80 - 2550 ้ที่กำหนดไม่น้อยกว่า 45 <mark>น</mark>าที ระ<mark>ยะเวลาการก่อตัวมีแนวโน้มล</mark>ดลงเมื่อปริมาณฝุ่นแอสฟัลท์เหลือทิ้ง เพิ่มขึ้น เนื่องจากขนา<mark>ดอนุ</mark>ภาคที่เล็กของฝุ่นแอสฟัลท์เหลือทิ้ง ทำให้ปริมาณน้ำบางส่วนถูกดูดซับบน ผิวอนุภาคของฝุ่นแอส<mark>ฟัลท์เห</mark>ลือทิ้ง ทำให้น้ำที่ใช้ในการเกิดปฏิกิริย<mark>าไฮเดร</mark>ชันกับปูนซีเมนต์มีน้อยลง ้ในทางกลับกันระยะเวลาการก่อตัวมีแนวโน้มเพิ่มขึ้นตามปริมาณเถ้าลอย เพราะปฏิกิริยาปอซโซลานิก ของเถ้าลอยเกิดขึ้นช้ากว่าปฏ<mark>ิกิริยาไฮเดรชันขอ</mark>งป<mark>ูนซีเมนต์ วัสดุซีเมน</mark>ต์ผสมทุกสูตรที่ระยะเวลาการ บ่ม 28 วัน จึงให้ค่ากำลังรับแรงอัดสูงกว่ามาตรฐานอุตสาหกรรม โดยการใช้ฝุ่นแอสฟัลท์เหลือทิ้งใน ปริมาณร้อยละ 20 ร่วมกับเถ้าลอยร้อยละ 30 ด้วยวิธีการบ่มวัสดุซีเมนต์ผสมภายใต้เงื่อนไขห่อหุ้ม ด้วยแผ่นพิล์มพลาสติก ส่งผลให้ได้ค่ากำลังรับแรงอัดสูงสุด เนื่องจากปฏิกิริยาไฮเดรชันและปฏิกิริยา ปอซโซลานิกที่ดำเนินไปอย่างต่อเนื่อง

สาขาวิชา <u>วิศวกรรมวัสดุ</u>	ลายมือชื่อนักศึกษา <del>พิมพ์ชนุ ()</del>
ปีการศึกษา2565	ลายมือชื่ออาจารย์ที่ปรึกษา

PIMCHANOK SERTSOONGNERN : THE USE OF ASPHALT WASTE DUST AND FLY ASH IN CEMENT-MIXED MATERIALS THESIS ADVISOR : ASSOC. PROF. JIRATCHAYA AYAWANNA, Ph.D., 64 PP.

## Keywords : CEMENT-MIXED MATERIALS/ ASPHALT WASTE DUST /FLY ASH/ COMPRESSIVE STRENGHT /CURING

Due to an environmental problem of the carbon dioxide ( $CO_2$ ) emission from the cement manufacturing industry, sustainable construction materials with the reduction of cement usage are being developed. Mixed cement material made of Portland cement type 1 with asphalt waste dust from asphalt concrete plants and fly ash from lignite coal-fired powe<mark>r sta</mark>tions wa<mark>s stu</mark>died. The mixed cement specimens were prepared from a fixed 50 wt% of Portland cement ratio, with 0 - 50 wt% of each asphalt waste dust and fly ash. Setting time and compressive strength test were carried out on the specimens after curing in lime-saturated water and in a plastic wrapping for 3, 7, and 28 days. After the strength test, microstructure and phase development of all specimens were examined. The initial setting time of all specimens passed the specified TIS 80 - 2007 standard, which is not less than 45 minutes. The setting time tended to reduce with an increase of asphalt waste dust due to the small particle size of asphalt waste dust, providing water is adsorbed on the surface of particles. As a result, less water for the hydration reaction of cement. Conversely, the setting time tended to increase with the fly ash content. This is because the pozzolanic reaction of fly ash takes place more slowly than the hydration reaction of cement. Mixed cement material at a curing period of 28 days, therefore, provided high compressive strength above the industry standard.

The use of 20 wt% asphalt waste dust with 30 wt% fly ash and curing by plastic wrapping generated the highest compressive strength as a result of continuous hydration reaction and pozzolanic reaction



School of <u>Material Engineering</u> Academic Year<u>2022</u> Student's Signature \_\_\_\_\_\_ Advisor's Signature\_\_\_\_\_\_