

# CONTENTS

	Page
ABSTRACT IN THAI.....	I
ABSTRACT IN ENGLISH.....	III
ACKNOWLEDGEMENTS.....	V
CONTENTS.....	VII
LIST OF FIGURES.....	X
LIST OF TABLES.....	XVIII
 <b>CHAPTER</b>	
<b>I      INTRODUCTION.....</b>	<b>1</b>
1.1    Background and Motivation.....	1
1.2    Research objectives.....	3
1.3    Outline of thesis.....	3
<b>II     LITERATURE REVIEWS .....</b>	<b>4</b>
2.1    Bismuth Ferrite (BiFeO <sub>3</sub> ) .....	4
2.1.1   Bismuth ferrite thin films preparation.....	5
2.1.2   Ferroelectric property in Bismuth ferrite thin films.....	7
2.1.3   Nanolithography on Bismuth ferrite thin films .....	9
2.2    Dynamic Mechanism.....	14
2.2.1   Photoelectric effect .....	14
2.2.2   Ferroelectric photovoltaic effect .....	15
2.3    Non Dynamic Mechanism.....	18
2.3.1   Electronic structures of two-dimensional electron gases.	18
2.3.2   Effects of oxygen vacancy.....	22

## CONTENTS (Continued)

	Page
<b>III RESEARCH METHODOLOGY.....</b>	<b>25</b>
3.1 Substrate Preparation.....	25
3.1.1 Substrate Cleaning.....	25
3.2 Thin film deposition and nanoscale patterning.....	26
3.2.1 BiFeO <sub>3</sub> thin film deposition.....	26
3.2.2 Nanoscale patterning of Metal oxide thin film.....	26
3.3 Basic characterization.....	30
3.3.1 X-ray diffraction (XRD).....	30
3.3.2 Scanning electron microscope (SEM).....	32
3.3.3 Optical profilometer.....	33
3.3.4 Energy-Dispersive X-ray Spectroscopy (EDS).....	33
3.3.5 Piezoresponse Force Microscopy (PFM).....	34
<b>IV RESULTS AND DISCUSSION.....</b>	<b>40</b>
4.1 Basic characterization.....	40
4.1.1 X-ray diffraction (XRD).....	40
4.1.2 Scanning electron microscope (SEM).....	41
4.1.3 Field emission scanning electron microscope (FESEM).....	43
4.1.4 Energy dispersive X-ray spectroscopy (EDS).....	45
4.2 Ferroelectric properties.....	46
4.2.1 Controlling the nano-scale ferroelectricity in unpatented area.....	46
4.2.2 Effect of nanopatterning on ferroelectricity.....	48
4.2.3 Effect of UV irradiation on ferroelectricity.....	52
4.3 Polarization-Electric field Hysteresis Loop (P-E loop).....	58
4.4 Voltage Response of Annealed BFO Film on NSTO Under Different UV Power Conditions.....	60

## CONTENTS (Continued)

	Page
V CONCLUSION AND FUTURE RESEARCH.....	62
5.1 Conclusions.....	62
5.2 Improvement and future research.....	64
REFERENCES.....	65
APPENDICES.....	75
APPENDIX A SUPPLEMENTARY RESULTS.....	76
APPENDIX B PUBLICATIONS AND PRESENTATIONS.....	93
CURRICULUM VITAE.....	95

## LIST OF FIGURES

Figure	Page
2.1 A diagram showing the rhombohedral structure of perovskite BFO, which belongs to the R3c space group, with two unit cells aligned along the [111] direction.....	5
2.2 The schematic diagram of the fundamental components of a magnetron sputtering system.....	7
2.3 The hysteresis loop of BFO/SRO/STO sample (a) at 15 kHz and (b) at orientation of (111), (101), and (001) BFO films.....	8
2.4 The hysteresis loop (a) BFO thin films different thicknesses of 190-600 nm on SRO/Pt/TiO <sub>2</sub> /SiO <sub>2</sub> /Si substrate at 1 kHz and (b) various electric fields of amorphous BFO thin films on Pt/Ti/SiO <sub>2</sub> /Si substrate.....	9
2.5 Schematic diagrams showing the DPN of BFO nanodots: (a) a nano-pattern using a BFO precursor sol by DPN, (b) BFO nanodots prepared on Nb-STO and HOPG substrates.....	10
2.6 The Principal of EBL.....	11
2.7 Differences in interaction volumes among various charged particle beams used for imaging.....	12
2.8 Piezoresponse measurement for (a) unpatterned BFO film and (b) 0.75 μm×0.5 μm patterned BFO structure. (c) Coercive voltage and (d) remanent piezoresponse of the patterned BFO structures and the unpatterned BFO film.....	14
2.9 The schematic diagram illustrates the ferroelectric photovoltaic device, (a) vertical and (b) lateral configurations.....	16

## LIST OF FIGURES (Continued)

Figure	Page
2.10 (a) The schematic setup for PFM and current density $J(E)$ measurements on Ag/BFO/Ag samples subjected to electric pulses of $\pm 150$ V (with an electric field $E \approx 17$ kV/cm). (b) The top panel shows the topography, and the middle and bottom panels display out-of-plane PFM images color-scaled after applying +150 V and -150 V pulses, respectively. (c) The $J(E)$ curves after applying different voltage pulses: +150 V, -150 V, and +150 V, respectively .....	17
2.11 The 2DEG states of La-doped STO after UV light exposure. (a) ARPES data of La-doped STO at $T = 20$ K, (b) Corresponding momentum distribution curves with parabolic fits to the data points. (c) Fermi surface map. (d) Schematic Fermi surface and band dispersions obtained from the electronic structure measurement.....	19
2.12 The presence of a 2DEG at the interface between BFO and STO is demonstrated using (a) a surface topography image and (b) nanoscale current tracing.....	20
2.13 Mechanisms of 2DEG formation and modulation in amorphous BFO/NSTO thin films Interface (a) the polarization-electric field (P-E) hysteresis loops of under UV illumination. This indicates the electrical polarization behavior which contributes to the formation of the 2DEG. (b) Illustrates the time-dependent voltage with UV irradiation cycles. This voltage difference is related to the induced electric field and polarization, crucial for understanding the modulation of 2DEG. (c)–(j): Provide schematic diagrams of UV-light-induced oxygen vacancies and the resultant quantum well states.....	21

## LIST OF FIGURES (Continued)

Figure	Page
2.14 The resistance of the STO surface was measured during the on-off UV irradiation. The measurement setup diagram is shown in the inset figure. Study by (a) Suwanwong et al. and (b) Jaiban et al. , provide the details of these measurements and setups, respectively.....	23
2.15 Coupling Mechanism between magnetic field and electric field or UV light via Kerr angle measurements in BFO films. (a) an applied magnetic field in units of Gauss and (b) an electric field or UV-light irradiation in units of W/m <sup>2</sup> . (c) Changes in the Kerr angle ( $\theta_B + \theta_E$ ) obtained from the applied magnetic field and electric field or UV-light irradiation. (d) A schematic illustrating the interaction between the magnetic field and the electric field or UV light through the Kerr-rotation measurement of the BFO film. (e) Changes in the states of BFO when an electric field, UV light, and a magnetic field are added or removed, measured in units of the Kerr angle...	24
3.1 Diagram illustrating the principle of FIB operation.....	27
3.2 Schematic of the BFO film on NSTO fabrication procedure. (a) Deposition BFO thin film by RF-sputtering, (b) The Annealing with temperature at 600 °C, (c) the process of patterning, (d) structures are acquired (e) Thermal treatments are designed to restore the crystalline nature of the structures and Gallium ion removal.....	28

## LIST OF FIGURES (Continued)

Figure	Page
3.3 The process for direct writing using EBL: (a) The electron beam resist is applied to the surface of the substrate using spin coating. b) A pattern is designed and then exposed onto the resist layer using an electron beam. (c) The sample undergoes a development process where the resist layer in the unexposed areas is removed, leaving behind the desired nanostructure pattern on the sample. (d) A thin layer of gold is deposited onto the patterned resist layer by electron beam evaporation. (e) The resist, along with the unwanted gold, is lifted off from the sample, revealing the gold pattern on the sample. (f) The sample is annealed at 120°C for 1 hour. This step helps to improve the crystallinity and adhesion of the gold layer to the substrate. ....	30
3.4 The illustration presents principal of X-ray diffraction.....	31
3.5 The sample preparation for PFM measurement.....	35
3.6 The phase image shows different polarization direction when voltage is applied to the sample surface. ....	36
3.7 The switching spectroscopy PFM: (a) DC triangle waveform, (b) local hysteresis loop result, and (c) the zoomed-in view of triangle waveform.....	37
4.1 (a) shows the XRD patterns of NSTO, BFO/NSTO unannealed and annealed samples. (b) shows the XRD patterns of FTO, BFO/FTO unannealed and annealed samples, and AuNHA. The figure displays the (100), (200), and (300) diffraction peaks of BFO films on both substrates.....	41
4.2 SEM images of (a) NSTO substrate, (b) BFO/NSTO sample in the RT condition with 3 minutes deposition time, (c) BFO/NSTO after annealing. The scale bar represents the length of 500 nanometers.....	42
4.3 SEM images of (a) FTO substrate, (b) BFO/FTO sample in the RT condition at a deposition time of 3 minutes, (c) BFO/FTO after annealing. The scale bar represents the length of 1 micrometer.....	42

## LIST OF FIGURES (Continued)

Figure	Page
4.4 SEM images of AuNHA on (a) FTO substrate, (b) BFO/FTO sample in the RT condition at a deposition time of 3 minutes. The scale bar represents the length of 1 micrometer. ....	43
4.5 FESEM images after patterned nanostructures of unannealed BFO/NSTO. The magnified images of square-shaped nanostructures are shown at (a) 1.6 kx and (b) 30 kx. The patterning field size is $40 \times 50 \mu\text{m}^2$ and grids size is $300 \times 400 \text{ nm}^2$ . The scale bars represent $10 \mu\text{m}$ and $500 \text{ nm}$ , respectively.....	44
4.6 EDS elemental analysis of (a) NSTO substrate, (b) BFO/NSTO unannealed, (c) BFO/NSTO annealed, (d) FTO substrate, (e) BFO/FTO unannealed and, (f) BFO/FTO annealed.....	46
4.7 PFM images showing the nano-letter patterns on the BFO/NSTO annealed surface. The top row displays PFM amplitude images, and the bottom row shows PFM phase images. The letters S,U, and T were created by applying +10 V over a $4 \times 4$ micrometer area (red color) and then -10 V to form the letters, each approximately 500 nm wide (blue color). The scan size for each image is 6 micrometers.....	47
4.8 PFM Images for un-patterned area (a) the topography, (b) PFM amplitude, and (c) PFM phase images after poling with +10V and -10V DC voltages. The hysteresis loops of BFO/NSTO annealed in the un-patterned area (d) amplitude, (e) phase, and (f) piezoresponse as functions of applied voltage. ....	49
4.9 PFM and hysteresis loops of nano-grid BFO/NSTO. The top row displays (a) topography, (b) PFM amplitude, and (c) phase images after poling with +10V and -10V DC voltages on a grid. The hysteresis loops for (d) amplitude, (e) phase, and (f) piezoresponse over applied voltage.....	50



## LIST OF FIGURES (Continued)

Figure	Page
4.10 PFM and hysteresis loop AuNHA/BFO/FTO (hole size 493 nm). The top row displays (a) topography, (b) amplitude, and (c) phase images, revealing the surface features and polarization states after poling with +10V and -10V DC voltages. The hysteresis loops for (d) amplitude, (e) phase, and (f) piezoresponse vs. applied voltage.....	51
4.11 PFM amplitude measurements of BFO film on NSTO under different UV states (poling -10V) : No UV (State 1), Under UV (State 2), and After UV (State 3). The top row displays the PFM amplitude images for each state, while the bottom row shows the mean and standard deviation (SD) of the amplitude for three areas (A1, A2, and A3) across the different states.....	54
4.12 PFM amplitude measurements after +10V poling of BFO film on NSTO under different UV states: No UV (State 1), Under UV (State 2), and After UV (State 3). The top row displays the PFM amplitude images for each state, while the bottom row shows the mean and standard deviation (SD) of the amplitude for three areas (A1, A2, and A3) across the different states.	55
4.13 PFM amplitude and phase measurements of BFO/NSTO annealed over time with +10V and -10V poling under No UV and Under UV conditions.....	57
4.14 The P-E hysteresis loops of BFO/NSTO annealed under different conditions: No UV (black line), Under UV (blue line), and After UV (green line). The graph plots polarization ( $\mu\text{C}/\text{cm}^2$ ) versus electric field (kV/cm)....	59
4.15 Voltage response over time for annealed BFO film on NSTO under different UV power conditions. The voltage was measured between the top and bottom electrodes. The graph shows the voltage response for UV power levels of 0.3 mW (black line), 14 mW (blue line), and 25 mW (green line). The voltage increases with UV ON and decreases with UV OFF, with higher UV power resulting in a greater photo-induced voltage response.....	61

## LIST OF FIGURES (Continued)

Figure	Page
A1 The PFM analysis of a standard PZT sample as a function of the applied voltage (V) .....	76
A2 PFM amplitude measurements of BFO/NSTO annealed under different UV states: No UV (State 1), Under UV (State 2), and After UV (State 3). The top row displays the PFM amplitude images for each state, while the bottom row shows the mean and standard deviation (SD) of the amplitude for three areas (A1, A2, and A3) across the different states.....	77
A3 PFM amplitude and phase measurements of BFO/NSTO annealed over time with -10V poling under No UV.....	78
A4 PFM amplitude and phase measurements of BFO/NSTO annealed over time with -10V poling under UV conditions.....	79
A5 PFM amplitude and phase measurements of BFO film on NSTO over time with +10V poling under No UV conditions.....	80
A6 PFM amplitude and phase measurements of BFO film on NSTO over time with +10V poling Under UV conditions.....	81
A7 piezoresponse over time of BFO film on NSTO over time with -10V and +10V poling Under no and UV conditions.....	81
A8 Plot of piezoresponse as a function of time for the annealed BFO/NSTO sample under three conditions: natural decay in darkness (green), infrared (IR) illumination (red), and UV illumination (blue).....	82
A9 Schematic diagram showing the DC poling process and the effect of UV light on oxygen vacancy formation at the BFO/NSTO interface: a) -10 V poling with indicated polarization direction, b) the state before UV exposure, and c) the state after UV exposure.....	83
A10 Commercial setup for PFM measurements.....	85
A11 PFM Hysteresis loop setup.....	86

## LIST OF FIGURES (Continued)

Figure	Page
A12 Piezoresponse over time of BFO film on NSTO over time with -10V and +10V poling Under no and UV conditions.....	87
A13 Data acquaintance and analysis algorithms.....	90
A14 Sample configuration for P-E loop measurement. The setup includes an NSTO substrate, a BFO thin film, Au/Cr layer, and Ag bottom electrode	91
A15 Voltage measurement sample configuration.....	92

## LIST OF TABLES

Table	Page
3.1 Sample's condition list for SEM measurement.....	32
4.1 Ferroelectric coefficient.....	52
4.2 UV irradiation conditions for -10V applied voltage.....	53