


รชานนท์ กลอนดอน : การกำจัดมลพิษทางอากาศด้วยกระบวนการโฟโตคะตะไลติก โดยเคลือบสารผสมไทเทเนียมไดออกไซด์และซิลิกอนไดออกไซด์บนผิวเครื่องปั้นดินเผาต้านเกวียน (REMOVAL OF AIR POLLUTANTS BY PHOTOCATALYTIC PROCESS USING TiO<sub>2</sub>-SiO<sub>2</sub> COATED DAN KWIAN POTTERY) อาจารย์ที่ปรึกษา : อาจารย์ ดร.สุพรรณิ จันทร์ภิรมณ์, 180 หน้า.

งานวิจัยนี้ศึกษาการเตรียมวัสดุตัวเร่งปฏิกิริยาผสมระหว่าง ไทเทเนียมไดออกไซด์ กับซิลิกอนไดออกไซด์ และนำไปเคลือบลงบนผิวเครื่องปั้นดินเผาต้านเกวียนเพื่อกำจัดมลพิษทางอากาศ ได้แก่ แก๊สคาร์บอนมอนอกไซด์และโอเบนซีนด้วยกระบวนการโฟโตคะตะไลซิส โดยแบ่งการศึกษาออกเป็น 5 ส่วนหลัก เริ่มจากส่วนแรกศึกษาการเตรียมซิลิกอนไดออกไซด์ จากแคลบข้าว โดยการนำแคลบแช่ในสารละลายกรด 3 ชนิด ได้แก่ กรดไฮโดรคลอริก กรดซัลฟิวริก และกรดไนตริก หลังจากนั้นนำไปเผาที่อุณหภูมิ 400-1,000°C ในส่วนที่สองศึกษาการเตรียมไทเทเนียมไดออกไซด์บริสุทธิ์ด้วยวิธีการโซล-เจล และสังเคราะห์ที่อุณหภูมิ 400-600°C ในส่วนที่สามศึกษาการเตรียมวัสดุตัวเร่งปฏิกิริยาผสมระหว่างไทเทเนียมไดออกไซด์และซิลิกอนไดออกไซด์ ในสัดส่วนต่าง ๆ ด้วยวิธีการโซล-เจล ส่วนที่สี่ศึกษาการเคลือบวัสดุตัวเร่งปฏิกิริยาผสมลงบนผิวเครื่องปั้นดินเผาต้านเกวียนด้วยวิธีการจุ่มเคลือบ ฟันเคลือบ และเคลือบด้วยวิธีของชาวบ้านต้านเกวียน และทดสอบประสิทธิภาพในกระบวนการโฟโตคะตะไลซิสโดยการสลายแก๊สคาร์บอนมอนอกไซด์จากควันธูป และโอเบนซีน สำหรับการศึกษาในส่วนสุดท้ายคือการจำลองกระบวนการโฟโตคะตะไลซิสเบื้องต้นโดยอาศัยวิธีการมอดลิ่งคาร์โด

ผลการศึกษาดังนี้ ในส่วนแรกพบว่าซิลิกอนไดออกไซด์บริสุทธิ์ที่เหมาะสมในงานวิจัยนี้เตรียมได้จากการแช่แคลบในสารละลายกรดซัลฟิวริกเข้มข้น 0.5M เผาที่อุณหภูมิ 600°C ให้ค่าพื้นที่ผิวจำเพาะสูงสุดเท่ากับ 301.76 m<sup>2</sup>/g ความบริสุทธิ์สูงเท่ากับ 98.4% ซึ่งมีโครงสร้างผลึกเป็นออสันฐาน ในส่วนที่สองพบว่าสภาวะที่เหมาะสมที่สุดในการเตรียมไทเทเนียมไดออกไซด์บริสุทธิ์ในงานวิจัยนี้คือสังเคราะห์ด้วยอุณหภูมิ 500°C ได้ไทเทเนียมไดออกไซด์บริสุทธิ์ 100% มีโครงสร้างผลึกเป็นอนาเทส 19.8% และรูไทล์ 80.2% มีขนาดอนุภาคเฉลี่ยประมาณ 10 μm และพื้นที่ผิวจำเพาะเท่ากับ 12.86 m<sup>2</sup>/g ซึ่งผลการทดสอบประสิทธิภาพในกระบวนการโฟโตคะตะไลซิส พบว่าสามารถสลายเมทิลีนบลูสูงสุดเท่ากับ 95.2% ในเวลา 12 ชั่วโมง ในส่วนที่สาม การเตรียมวัสดุตัวเร่งปฏิกิริยาผสม ซึ่งเตรียมด้วยสภาวะเดียวกับการเตรียมไทเทเนียมไดออกไซด์บริสุทธิ์ พบว่าสัดส่วนของปริมาณไทเทเนียมไดออกไซด์ต่อซิลิกอนไดออกไซด์เท่ากับ 1 : 1 ให้ประสิทธิภาพในการสลายเมทิลีนบลูสูงสุดเท่ากับ 95.5% ในเวลา 3 ชั่วโมง และสามารถหาความสัมพันธ์กับสมการแลงเมียร์-

อินเซลวูด โดยมีค่าคงที่  $K_{LH}=0.261$  L/mg และค่า  $k_r=0.135$  mg/L-min ผลการศึกษาในส่วนที่สี่ซึ่งทำการเคลื่อนตัวเร่งปฏิกิริยาผสมสัดส่วน 1:1 ลงบนผิวเครื่องปั้นดินเผาต้านเกวียนด้วยวิธีการที่แตกต่างกัน 3 วิธี พบว่าวิธีการเคลื่อนแบบจุ่มเคลื่อนและพ่นเคลื่อน ด้วยสูตรผสมที่ 2 (ตัวเร่งปฏิกิริยาผสม 4 กรัมและผงดินละเอียด 3 กรัม) มีประสิทธิภาพในการสลายแก๊สคาร์บอนมอนอกไซด์ใกล้เคียงกันคือ 6.7 และ 7.4% ในเวลา 5 ชั่วโมง ตามลำดับ สำหรับการทดสอบการสลายไอเบนซีน ทดสอบโดยใช้ชิ้นงานเครื่องปั้นดินเผาต้านเกวียนที่เคลื่อนด้วยสูตรที่ 2 ของวิธีจุ่มเคลื่อน พบว่ามีแก๊สคาร์บอนไดออกไซด์เกิดขึ้นจากการสลายไอเบนซีนเท่ากับ 0.3% และผลการศึกษาในส่วนท้ายสุด การจำลองกระบวนการโฟโตคะตะไลซิสอย่างง่าย พบว่าตัวแปรที่มีผลต่อประสิทธิภาพของกระบวนการโฟโตคะตะไลซิสคือขนาดของระบบจำลอง ระยะทางในการจำลองการเคลื่อนที่ของแต่ละโมเลกุล และปริมาณตัวเร่งปฏิกิริยาในระบบจำลอง



RACHANON KLONDON : REMOVAL OF AIR POLLUTANTS BY  
PHOTOCATALYTIC PROCESS USING  $\text{TiO}_2\text{-SiO}_2$  COATED DAN KWIAN  
POTTERY. THESIS ADVISOR : SUPUNNEE JUNPIROM, Ph.D., 180 PP.

PHOTOCATALYTIC PROCESS/SEMICONDUCTOR/ $\text{TiO}_2/\text{SiO}_2$ /DAN-KWIAN  
POTTERY/MONTE CARLO SIMULATION

This work aimed to study the preparation of  $\text{TiO}_2\text{-SiO}_2$  composite photocatalyst. This photocatalyst was coated on Dan Kwian pottery and applied to degrade air pollutants i.e. carbon monoxide ( $\text{CO}$ ) and benzene vapor ( $\text{C}_6\text{H}_6$ ) by photocatalysis. There are five main parts of this work. The first part is the preparation of  $\text{SiO}_2$  from rice husk by impregnation in different 3 acids and further calcination at temperature in the range of  $400\text{-}1,000^\circ\text{C}$ . These acids are  $\text{HCl}$ ,  $\text{H}_2\text{SO}_4$  and  $\text{HNO}_3$ . The second part is  $\text{TiO}_2$  preparation by using sol-gel method with variation of calcination temperature between  $400\text{-}600^\circ\text{C}$ . The third part is the preparation of composite photocatalyst by adding  $\text{SiO}_2$  into  $\text{TiO}_2$  preparation process with variation the mass ratio of  $\text{TiO}_2$  and  $\text{SiO}_2$ . The fourth part is the study of the coating effect of composite photocatalyst on the Dan Kwian pottery surface by using dip coating, spray coating and hand coating. The photocatalytic activity of coated samples was investigated by degradation of  $\text{CO}$  generated from incense and  $\text{C}_6\text{H}_6$ . Finally, the last part is the preliminary study on simple simulation of pollutant degradation by the photocatalysis based on Monte Carlo algorithms.

The first part gave the optimum condition to prepare the  $\text{SiO}_2$  which is the impregnation with  $0.5\text{M}$  of  $\text{H}_2\text{SO}_4$  and calcination at  $600^\circ\text{C}$ . The obtained  $\text{SiO}_2$  has

highest specific surface area of  $301.76 \text{ m}^2/\text{g}$ , 98.4% purity with an amorphous structure. The second part provided the optimum condition to produce  $\text{TiO}_2$  is calcination at  $500^\circ\text{C}$ . Structure of this  $\text{TiO}_2$  was found to consist of 19.8% anatase and 80.2% rutile, with an average particle size of  $10 \mu\text{m}$  and specific surface area of  $12.86 \text{ m}^2/\text{g}$ . Its photocatalytic activity for methylene blue (MB) degradation is 95.2% for 12 hours. In the third part, the composite photocatalyst of the  $\text{TiO}_2\text{-SiO}_2$  mass ratio 1:1 gave the highest efficiency of 95.5% MB degradation within 3 hours. The experimental data are in good agreement with Langmuir-Hinshelwood equation with the optimized parameters of  $K_{\text{LH}}=0.261 \text{ L/mg}$  and  $k_{\text{r}}=0.135 \text{ mg/L-min}$ . This best composite photocatalyst was then selected to coat on the surface of Dan Kwian pottery with 3 different methods for coating. It was found that the dip coating and spray coating with the coated slip No.2 (4g of composite photocatalyst and 3g of clay) gave the similar efficiency of CO degradation for 6.7 and 7.4% within 5 hours, respectively. The dip coated surface was further used to degrade the  $\text{C}_6\text{H}_6$  vapor. It was observed that the  $\text{CO}_2$  was generated about 0.3% during the  $\text{C}_6\text{H}_6$  degradation. From the last part, the photocatalytic process can be simulated by the Monte Carlo simulation. The main parameters of the simulation are the system volume, the moving distance of molecules and the catalyst loading.

School of Chemical Engineering

Academic Year 2013

Student's Signature \_\_\_\_\_

Advisor's Signature \_\_\_\_\_