

อภิชาติ เกียนสารน้อย : การปรับปรุงคุณสมบัติของพอลิแลคติกแอซิดสำหรับการใช้งานที่
อุณหภูมิต่ำ (POLYLACTIC ACID COMPOUNDING FOR SUB ZERO
TEMPERATURE APPLICATIONS) อาจารย์ที่ปรึกษา : ผู้ช่วยศาสตราจารย์ ดร.อุทัย มีคำ,
169 หน้า.

การศึกษาการผสมระหว่างพอลิแลคติกแอซิด(polylactic acid, PLA) กับยางซิลิโคน
(silicone rubber) ชนิด 2 และ 1 องค์ประกอบโดยใช้การศึกษาเชิงสถิติ ด้วยวิธีการออกแบบการ
ทดลอง(Design of Experiment, DOE) ของการผสมในระบบของซิลิโคนชนิด 2 องค์ประกอบ
พบว่าซิลิโคนส่งผลเชิงบวก และ มีผลอย่างมีนัยสำคัญต่อค่าความแข็งเหนียวของพอลิเมอร์ผสมที่
เตรียมได้ ทั้งที่การทดสอบที่อุณหภูมิห้องและอุณหภูมิต่ำกว่าจุดเยือกแข็ง พอลิเมอร์ผสมระหว่าง
พอลิแลคติกแอซิดกับยางซิลิโคนชนิด 2 องค์ประกอบ ที่มีไซเลน(silane) ทำหน้าที่เป็นสารกู้คืน
และ พอลิօอล ชนิด พอลิเอสเทอร์(polyester polyol) ทำหน้าที่เป็นพลาสติไซเซอร์ พบว่าการใช้
ซิลิโคนที่ 8.0 ส่วนในร้อยส่วน โดยน้ำหนัก มีผลทำให้คุณสมบัติที่ดีในทุกๆ ค่าการทดสอบ การเติม
สารเพื่อการคงรูปของซิลิโคนชนิด ไตรเอทธิลเทเรฟโนเมิน(TETA) ที่ปริมาณต่ำกว่า 0.4 ส่วนใน
ร้อยส่วน โดยน้ำหนักของซิลิโคน ช่วยเพิ่มคุณสมบัติการทนต่อแรงดึงดีดีขึ้น พอลิเมอร์ผสม
ระหว่างพอลิแลคติกแอซิด กับ ยางซิลิโคนชนิด 2 องค์ประกอบ สามารถยืดสลายตัวเชิงชีวภาพได้
ภายใน 4 สัปดาห์ การผสมระหว่างพอลิแลคติกแอซิด กับ ยางซิลิโคนชนิด 1 องค์ประกอบ ที่
ปริมาณการใช้ซิลิโคนเท่ากับ 8.0 ส่วนในร้อยส่วน โดยน้ำหนัก ทำให้ได้พอลิเมอร์ผสมที่มี
คุณสมบัติที่ดีเมื่อเปรียบเทียบกับแอลดีพีอี (LDPE) โดยเฉพาะคุณสมบัติการทนต่อแรงตកกระแทก
ที่อุณหภูมิต่ำกว่าจุดเยือกแข็ง การผสมระหว่างพอลิแลคติก แอซิด กับยางซิลิโคนชนิด 1
องค์ประกอบ ที่มีการเติมผงตัวเดิมชนิดทาลคัม(Talc) ลงไปในอัตราส่วน 40 ส่วนในร้อยส่วนโดย
น้ำหนัก สามารถนำไปทดสอบการเป้าขึ้นรูปเป็นฟิล์มได้ ในระดับที่การควบคุมกระบวนการเป้า
ฟิล์มกระทำได้ยาก แต่สามารถเป้าขึ้นรูปได้

APICHART KHIANSANOI : POLYLACTIC ACID COMPOUNDING FOR
SUB ZERO TEMPERATURE APPLICATIONS. THESIS ADVISOR :
ASST. PROF. UTAI MEEKUM, Ph.D., 169 PP.

POLY(LACTIC ACID)/ LOW TEMPERATURE IMPACT STRENGTH/ SILICONE
RUBBER/ TALC/ MECHANICAL PROPERTIES/ BIODEGRADABILITY

The blends between PLA with two and single component silicone rubbers were studied, respectively. Statistical, 2^K factorial DOE, results showed that the silicone was positively and significantly improved the fracture toughness, at room and sub zero temperature, of the PLA and two components silicone rubber blend having silane as coupling agent and polyester polyols as plasticizer. Further refinement indicated that the blend manifested better overall properties at 8.0 phr of the silicone rubber content. The tensile properties of the PLA/silicone rubber blend were enhanced by adding not more than 0.4 phr of TETA. The initial observation revealed that the PLA/silicone rubber blend can be biologically degraded within four weeks.

The blend between PLA and single component silicone rubber at 8.0 phr of the silicone rubber fraction showed adequate properties, especially impact strength at sub zero temperature, when compare with LDPE blow film grade. The PLA/silicone rubber blend having 40 phr of talc filler was chosen to perform the blown film process. It was observed that blown film process was feasible with great difficulty to control the stability of the film bubble.

School of Polymer Engineering

Academic Year 2011

Student's Signature Apichart
Advisor's Signature M.Uta