

วรรณพงศ์ คล่องแฉล่ว : การศึกษาความสัมพันธ์ของกำลังรับแรงอัดกับอายุวัสดุที่ใช้ในการบูรณะทางผิวทางแอสฟัลต์ โดยวิธี PAVEMENT IN-PLACE RECYCLE (A COMPRESSION TEST OF RESTORED MATERIALS FROM THE PAVEMENT IN-PLACE RECYCLE) อาจารย์ที่ปรึกษา : ผู้ช่วยศาสตราจารย์ ดร.วชรภูมิ เบญจโภพ

งานวิจัยนี้ศึกษาความสัมพันธ์ของกำลังรับแรงอัดกับอายุบ่ำของวัสดุทางเดินที่ใช้ในงานบูรณะทางผิวทางแอสฟัลต์ โดยวัสดุทางเดินประกอบด้วยผิวทาง Asphalt concrete และพื้นทางหินคลุก ผสมรวมกันแล้วนำวัสดุทางเดินผสมกับปูนซีเมนต์ปอร์ตแลนด์ให้ได้อัตราส่วนที่สามารถทำให้ปรับปรุงคุณภาพวัสดุพื้นทางเดินให้มีกำลังรับแรงอัดได้ไม่น้อยกว่า 24.5 กิโลกรัมต่อตารางเซนติเมตร ในอายุบ่ำที่ 7 วันตามมาตรฐานกำหนด ซึ่งในงานวิจัยนี้ได้ใช้วัสดุทางเดินจาก 4 สายทาง ในการศึกษาหาความสัมพันธ์ของกำลังรับแรงอัดกับอายุบ่ำที่ 24,72,120,168 และ 216 ชั่วโมงในห้องปฏิบัติการ เพื่อนำผลการทดสอบกำลังรับแรงอัดตามอายุบ่ำของแผนกราฟทดลองมาเปรียบเทียบและวิเคราะห์กับข้อกำหนดตามมาตรฐานการหมุนเวียนวัสดุชั้นทางเดินกลับมาใช้งานใหม่

จากผลการทดสอบกำลังรับแรงอัดของตัวอย่างทั้ง 4 สายทาง ในห้องปฏิบัติการ จะได้สมการกำลังอัดเฉลี่ย $y = 0.087x + 21.07$ และค่า $R^2 = 0.533$ ซึ่งพยากรณ์ได้ว่ากำลังรับแรงอัดที่อายุบ่ำ 168 ชั่วโมง มีค่าเป็น 1.23 เท่าของกำลังรับแรงอัดที่อายุบ่ำ 72 ชั่วโมง และสมการกำลังอัดต่ำที่สุด $y = 0.040x + 16.03$ มีค่า $R^2 = 0.960$ อัตราส่วนเท่ากับ 1.20 เท่า ผลการศึกษานี้ได้ค่าพยากรณ์ กำลังรับแรงอัด เพื่อนำไปเป็นข้อมูลในการพัฒนาการบูรณะทางผิวทางแอสฟัลต์ ในการบริหารจัดการงานสนามในโอกาสต่อไป

WANNAPONG KHLONGKHLAEO : A COMPRESSION TEST OF RESTORED MATERIALS FROM THE PAVEMENT IN-PLACE RECYCLE.
THESIS ADVISER: ASST. PROF. VACHARAPOOM BENJAORAN, Ph.D.

The research studies the relationships of compressive strength with ages of recycling pavement materials. The restored materials consist of asphalt-concrete pavement and base – course aggregate. These restored materials are then mixed with Portland cement using a suitable ratio to improve the compressive strength of the original base-course aggregate. The acceptable strength standard is not less than 24.5 kg./cm.² at the curing age of 7 days. This research conducted a test that use the restored materials from 4 different highways. The compression test of these restored materials way conducted at the curing ages of 24, 72, 120, 168 and 216 hours in laboratory. The test results were compared and analyzed with the highway standard of the pavement in- place recycling.

The test results indicate the relationship equation of the average compressive strength as $y = 0.087x+21.07$ and $R^2 = 0.533$. This provided the ratio of compressive strength at 168 hours to 72 hours of ages as 1.23. The relationship equation of the lowest compressive strength is $y = 0.040x+16.03$ and $R^2 = 0.960$ and the ratio of compressive strength at 168 hours to 72 hours of ages is 1.20. The finding from this research can be use for forecasting the compressive strength of the restored pavement materials at the early age of 168 hours using the strength at the age of 72 hours .This can reduce the waiting time for the strength test in the field and expedite the renovation of the highway.

School of Civil Engineering
Academic Year 2010

Student's Signature _____
Advisor's Signature _____