

## บทคัดย่อภาษาไทย

เพื่อปรับปรุงประสิทธิภาพการบรรจุระดับนาโนของ  $\text{LiBH}_4$  และ  $\text{MgH}_2$  ในวัสดุคาร์บอนที่มีรูพรุนระดับนาโนเมตร (carbon aerogel scaffold, CAS) โดยวิธีการลดขนาดอนุภาคของ  $\text{MgH}_2$  ด้วยการบด  $\text{MgH}_2$  ก่อนการบรรจุ โดย  $\text{MgH}_2$  ถูกบดก่อนเป็นเวลา 5 ชั่วโมง แล้วบดผสมกับ  $\text{LiBH}_4$  และทำการบรรจุระดับนาโนเมตร (nanoconfinement) ในรูพรุนของ CAS ได้เป็นตัวอย่าง nanoconfined  $2\text{LiBH}_4$ -premilled  $\text{MgH}_2$  เทคนิค  $\text{N}_2$  adsorption-desorption และ SEM-EDS-mapping ยืนยันว่าประสิทธิภาพการบรรจุระดับนาโนเมตรของสารประกอบไฮโดรเจนขึ้นเมื่อมีการบด  $\text{MgH}_2$  ก่อนการบรรจุ กลไกการเกิดปฏิกิริยาปลดปล่อยไฮโดรเจนของตัวอย่าง nanoconfined  $2\text{LiBH}_4$ -premilled  $\text{MgH}_2$  พบว่าเกิดเพียงขั้นตอนเดียวที่อุณหภูมิ  $345^\circ\text{C}$  ในขณะที่ตัวอย่างที่ไม่ได้บด  $\text{MgH}_2$  ก่อนการบรรจุ เกิดปฏิกิริยาหลายขั้นตอนที่อุณหภูมิสูงถึง  $430^\circ\text{C}$  และยังปล่อยก๊าซ  $\text{B}_2\text{H}_6$  ออกมาด้วยในระหว่างการเกิดปฏิกิริยา นอกจากนี้ค่าพลังงานก่อกัมมันต์ที่เกี่ยวข้องกับปฏิกิริยาปลดปล่อยไฮโดรเจนของตัวอย่างลดลงอย่างมีนัยสำคัญเมื่อมีการบด  $\text{MgH}_2$  ก่อนการบรรจุ ( $\Delta E_A = 31.9$  และ  $55.8$  kJ/mol ของ  $\text{LiBH}_4$  และ  $\text{MgH}_2$  ตามลำดับ) ซึ่งส่งผลให้อัตราเร็วของปฏิกิริยาดังกล่าวเพิ่มขึ้นประมาณสองเท่า เมื่อดำเนินปฏิกิริยาปลดปล่อยไฮโดรเจนที่  $320^\circ\text{C}$  ความดันไฮโดรเจน 3-4 บาร์ พบว่าตัวอย่าง nanoconfined  $2\text{LiBH}_4$ -premilled  $\text{MgH}_2$  ปล่อยก๊าซไฮโดรเจนออกมได้ถึง 4.96 wt. % ในขณะที่ตัวอย่างที่ไม่ได้บด  $\text{MgH}_2$  ก่อนปล่อยก๊าซออกมาเพียง 4.30 wt. % ซึ่งเป็นปริมาณของก๊าซผสมระหว่างไฮโดรเจนและ  $\text{B}_2\text{H}_6$  ดังนั้นตัวอย่าง nanoconfined  $2\text{LiBH}_4$ -premilled  $\text{MgH}_2$  นอกจากจะช่วยเพิ่มอัตราเร็วในการเกิดปฏิกิริยาแล้วยังยับยั้งการปลดปล่อยก๊าซ  $\text{B}_2\text{H}_6$  ด้วย รวมถึงสามารถเกิดปฏิกิริยาปลดปล่อยไฮโดรเจนที่อุณหภูมิต่ำ ( $T = 320^\circ\text{C}$ ) กว่าระบบ  $2\text{LiBH}_4$ - $\text{MgH}_2$  ระบบอื่นๆ ที่มีการพัฒนาก่อนหน้านี้

### บทคัดย่อภาษาอังกฤษ

To improve nanoconfinement of  $\text{LiBH}_4$  and  $\text{MgH}_2$  in carbon aerogel scaffold (CAS), particle size reduction of  $\text{MgH}_2$  by premilling technique before melt infiltration is proposed.  $\text{MgH}_2$  is premilled for 5 h prior to milling with  $\text{LiBH}_4$  and nanoconfinement in CAS to obtain nanoconfined 2 $\text{LiBH}_4$ -premilled  $\text{MgH}_2$ . Significant confinement of both  $\text{LiBH}_4$  and  $\text{MgH}_2$  in CAS, confirmed by SEM-EDS-mapping results, is achieved due to  $\text{MgH}_2$  premilling. Due to effective nanoconfinement, enhancement of CAS:hydride composite weight ratio to 1:1, resulting in increase of hydrogen storage capacity, is possible. Nanoconfined 2 $\text{LiBH}_4$ -premilled  $\text{MgH}_2$  reveals a single-step dehydrogenation at 345 °C with no  $\text{B}_2\text{H}_6$  release, while dehydrogenation of nanoconfined sample without  $\text{MgH}_2$  premilling performs in multiple steps at elevated temperatures (up to 430 °C) together with considerable amount of  $\text{B}_2\text{H}_6$  release. Activation energy ( $E_A$ ) for the main dehydrogenation of nanoconfined 2 $\text{LiBH}_4$ -premilled  $\text{MgH}_2$  is considerably lower than those of  $\text{LiBH}_4$  and  $\text{MgH}_2$  of bulk 2 $\text{LiBH}_4$ - $\text{MgH}_2$  ( $\Delta E_A = 31.9$  and 55.8 kJ/mol with respect to  $\text{LiBH}_4$  and  $\text{MgH}_2$ , respectively). Approximately twice faster dehydrogenation rate are accomplished after  $\text{MgH}_2$  premilling. Three hydrogen release ( $T=320$  °C,  $P(\text{H}_2)=3-4$  bar) and uptake ( $T=320-325$  °C,  $P(\text{H}_2)=84$  bar) cycles of nanoconfined 2 $\text{LiBH}_4$ -premilled  $\text{MgH}_2$  reveal up to 4.96 wt. %  $\text{H}_2$  (10 wt. %  $\text{H}_2$  with respect to hydride composite content), while the 1<sup>st</sup> desorption of nanoconfined sample without  $\text{MgH}_2$  premilling gives 4.30 wt. % of combined  $\text{B}_2\text{H}_6$  and  $\text{H}_2$  gases. It should be remarked that not only kinetic improvement and  $\text{B}_2\text{H}_6$  suppression are obtained by  $\text{MgH}_2$  premilling, but also the lowest dehydrogenation temperature ( $T=320$  °C) among other modified 2 $\text{LiBH}_4$ - $\text{MgH}_2$  systems is acquired.